



## GRAFTABOND™ EV-GMA 15025 IM

Ethylene – Vinyl Acetate copolymer grafted with Glycidyl Methacrylate and Methyl Methacrylate

### Product Data

#### Description

GRAFTABOND™ EV-GMA 15025 IM is a copolymer of ethylene, so it's compatible with polyethylene and with most other ethylene copolymers. The vinyl acetate brings flexibility, softness and polarity to the material, and glycidyl methacrylate adds reactive groups to GRAFTABOND™ EV-GMA 15025 IM.

#### Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Characteristics	Value	Unit	Test Method
Vinyl Acetate content	28	%	FTIR (Internal Method)
Acrylate content	≈5	%	FTIR (internal method)
Melt Flow Index (190°C / 2,16 kg)	≈150*	g/10min	ISO 1133 / ASTM D1238
Drying Loss (105 °C)	<0,5	%	ASTM D6980
Melting point	59	°C	ISO 11357-3

(\*) can be regulated to customer needs

**Supplied as:** Granulate

# GRAFTABOND™ EV-GMA 15025 IM

## Product Data Sheet

---

### Applications

- GRAFTABOND™ EV-GMA 15025 IM is designed for PVC impact modification

### Processing

- GRAFTABOND™ EV-GMA 15025 IM is processable on most thermoplastics processing equipment,
- Preferable for: Compounding PVC transparent films (Extruding)
- Purge the equipment after a run is completed.

### Storage and Transportation

MSDS provided to recommend safe practices during use and storage. Improper storage conditions may cause degradation and have consequences on physical properties of the product. For easy handling and storage normally packed in 25 kg bags (50 bags per pallet).

Due to its physical properties (Vicat temperature <40°C), the product may agglomerate, especially in hotter storage conditions.

**Shelf Life:** Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The data listed here falls within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The GRAFT POLYMER Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of GRAFTABOND™ or others. Since GRAFT POLYMER cannot anticipate all variations in actual end-use conditions, GRAFT POLYMER makes no warranties and assumes no liability in connection with any use of this information.

---

#### GRAFT POLYMER D.O.O.

Emonska Cesta 2, Ljubljana Slovenia.  
Company Num. 8056200000, VAT. SI 30561345  
Phone Num. +38640867937  
[office@graftpolymer.com](mailto:office@graftpolymer.com)

#### GRAFT POLYMER UK LTD

Central Working Victoria Ecclestone Yards 25,  
Ecclestone Pl, London, UK, SW1W 9NF.  
Company Num. 10776788, VAT. 281712016  
[www.graftpolymer.com](http://www.graftpolymer.com)