



GRAFTAPOR™ EVA 00380

Porous Ethylene-Vinyl Acetate Copolymer Carrier

Product Data

Description

GRAFTAPOR™ EVA 00380 is a porous polymer carrier for additives, made from EVA resin. It's mainly designed to act as a carrier for additives that are harder to dose during polymer compounding.

Typical Properties

The values indicated in this data sheet describe typical properties and do not constitute specification limits.

Characteristics	Value	Unit	Test Method
Vinyl-Acetate Content	28	%	Graft Polymer Internal Method
Melting point	88	°C	ISO 11357-3
Density	0,190	g/cm ³	ISO 1183 / ASTM D0035
Porosity	>80*	%	Graft Polymer Internal Method

(*) can be adjusted to customer needs.

Supplied as: Granulate

Applications

- GRAFTAPOR™ EVA 00380 is used to make polymer compounding easier, by absorbing liquid, powder, low melting or thermally sensitive additives.
- Can absorb solid or paste additives, with melting point up to 40°C below the melting point of GRAFTAPOR™ EVA 00380.

Processing

- For the loading of additives into GRAFTAPOR™ EVA 00380, mix at low rpm (5-30 rpm) and at loading time from 30 min up to 72 h.
- Absorption time depends on the viscosity of additive.
- At higher loading temperatures and faster mixing, the porous structure may collapse.
- Up to 80% of additive content can be loaded onto the polymer carrier.

Storage and Transportation

MSDS provided to recommend safe practices during use and storage. Improper storage conditions may cause degradation and have consequences on physical properties of the product. For easy handling and storage normally packed in 7 kg bags (Up to 50 bags per pallet).

Shelf Life: Two years from the date of delivery, in unopened packaging. For any use above this limit, please refer to our technical services.

The data listed here falls within the normal range of properties, but they should not be used to establish specification limits nor used alone as the basis of design. The GRAFT POLYMER Company assumes no obligations or liability for any advice furnished or for any results obtained with respect to this information. All such advice is given and accepted at the buyer's risk. The disclosure of information herein is not a license to operate under, or a recommendation to infringe, any patent of GRAFTAPOR™ or others.

GRAFT POLYMER D.O.O.

Emonska Cesta 2, Ljubljana Slovenia.
Company Num. 8056200000, VAT. SI 30561345
Phone Num. +38640867937
office@graftpolymer.com

GRAFT POLYMER UK LTD

Central Working Victoria Ecclestone Yards 25,
Ecclestone Pl, London, UK, SW1W 9NF.
Company Num. 10776788, VAT. 281712016
www.graftpolymer.com